

## PRODUCT SHEET

## STEPPING S3 SRC

 Prod. Ref.
 TN290-000

 Safety cat.
 S3 SRC

 Range of sizes
 38 - 48 (5 - 13)

 Weight (sz. 8)
 650 g

 Shape
 B

 Widht (5 - 6)
 10,5

 Widht (6,5 - 13)
 11

**Description:** Brown water repellent nubuck ankle boot, **TRAI-Tex** 100% polyester fabric lining, anti-shock, antistatic, slipping resistant, non metallic **APT Plate** midsole **Zero Perforation** 

**Plus: METAL FREE. EVANIT** footbed, made of EVA and nitrile special compound, with high bearing capacity and variable thickness. Thermoformed, punched and coated with highly breathable fabric. Antistatic thanks to a specific treatment on the surface and to seams made of conductive yarns

Suggested uses: Construction, maintenance, industries

Care and maintenance: Clean after each use and dry off away from direct heat. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water



## MATERIALS / ACCESSORIES

## SAFETY TECHNICAL SPECIFICATIONS

			Clause EN ISO 20345:2011	Description	Unit	Cofra result	requirement
Complete shoe	Toe cap: non	metallic FIBERGLASS toe cap, impact resistant until 200 J	5.3.2.3	Shock resistance (clearance after shock)	mm	15,5	≥ 14
	an	d compression resistant until 1500 kg	5.3.2.4	Compression resistance (clearance after compression)	mm	19,5	≥ 14
	Anti perforation midsole: in multi-layers highly tensile fabric, penetration resistant, Zero Perforation		6.2.1	Penetration resistance	N	To 1100 N	≥ 1100
	Perioration					No Perforation	
	Antistatic shoe: the bottom is fit for the dissipation of electrostatic charges		6.2.2.2	Electric resistance			
				- wet	$M\Omega$	70,2	≥ 0.1
				- dry	$M\Omega$	290	≤ 1000
	Energy absor	ption system	6.2.4	Shock absorption	J	35	≥ 20
Upper	Brown water r	epellent nubuck	5.4.6	Water vapour permeability	mg/cmq h	> 4,5	≥ 0,8
	thickness 1,6/	1,8 mm		Permeability coefficient	mg/cmq	> 43,8	> 15
			6.3.1	Water absorption		20%	≤ 30%
				Water penetration		0,0 g	≤ 0,2 g
Vamp	Felt, breathable, colour dark grey		5.5.3	Water vapour permeability	mg/cmq h	> 4,2	≥ 2
lining	Thickness 1,2 mm			Permeability coefficient	mg/cmq	> 47,7	≥ 20
Quarter	TRAI-Tex fabric, three-dimensional, breathable, abrasion resistant, colour black		5.5.3	Water vapour permeability	mg/cmq h	> 4,1	≥ 2
lining	thickness 1,2 mm			Permeability coefficient	mg/cmq	> 47,2	≥ 20
Sole	Antistatic dual-density Polyurethane directly injected in the upper:		5.8.3	Abrasion resistance (lost volume)	$mm^3$	98	≤ 150
	Outsole:	black, high density, slipping resistant, abrasion	5.8.4	Flexing resistance (cut increase)	mm	4	≤ 4
		resistant and hydrocarbons resistant,	5.8.5	Interlayer bond strength	N/mm	4,1	≥ 3
	Midsole:	black, low density, comfortable and anti-shock	6.4.2	Hydrocarbons resistance ( $\Delta V$ = volume increase)	%	8	≤ 12
	Adherence co	efficient of the sole	5.3.5	SRA: ceramic + detergent solution - flat		0,33	≥ 0,32
				SRA : ceramic + detergent solution - heel (contact angle 7°)		0,30	≥ 0,28
				SRB : steel + glycerol – flat		0,18	≥ 0,18
				SRB : steel + glycerol – heel (contact angle 7°)		0,15	≥ 0,13